

# GENESIS®



**WITH PROVEN  
ARAMID  
PERFORMANCE**

**GENESIS®**

**4.5 osy (155 gsm) / 6.0 osy (205 gsm)**

### **ARAMID FIBER BLEND**

Inherently flame-resistant fabric with tri-blend comprised of 93% Meta-Aramid, 5% Para-Aramid, and 2% Anti-Static fiber.

### **LIGHT AND COMFORTABLE**

Genesis® fabrics are tough, yet light and comfortable to wear. Proprietary wicking finish stays soft, keep cool and dry.

### **TOUGH AND ROBUST**

Heavy-duty garments made from Genesis fabrics retain their looks even after repeated high-temperature industrial laundering.

 **TENCATE**  
protectivefabrics

*made for life*

# GENESIS®

GENERAL ATTRIBUTES	450	600
Nominal Weight	155 gsm	205 gsm
Construction	Plain Weave	Plain Weave
Fiber Content	Meta-Aramid, Para-Aramid and Anti-Static	Meta-Aramid, Para-Aramid and Anti-Static
Finish	Wickwell™ Plus	Wickwell™ Plus
Certifications	NFPA 2112	NFPA 2112
PROTECTION	450	600
Electric Arc Rating ASTM 1959	4.6 cal/cm <sup>2</sup> - 4.8 cal/cm <sup>2</sup>	5.7 cal/cm <sup>2</sup> - 5.9 cal/cm <sup>2</sup>
Personal Protective Equipment (PPE) NFPA 70E	PPE1	PPE1
Thermal Protective Performance (TPP) With Spacer Without Spacer NFPA 2112 Standard: With 6.0 Minimum, Without 3.0 Minimum	10.5 cal/cm <sup>2</sup> 5.5 cal/cm <sup>2</sup>	12.0 cal/cm <sup>2</sup> 6.2 cal/cm <sup>2</sup>
Flame Resistance Char Length After Flame ASTM 6413, NFPA 2112 Standard: 4.0 in Maximum, 2 Sec Maximum	< 4.0 in (< 10.0 cm) < 2 Sec	< 4.0 in (< 10.0 cm) < 2 Sec
Thermal Shrinkage (Before Laundering) NFPA 2112 Standard: 10% Max	3.0%	3.0%
FABRIC STRENGTH	450	600
Tensile Strength ASTM D 5034	855 N x 536 N	1,190 N x 725 N
Elmendorf Tear Strength ASTM D 1424	58 N x 37 N	65 N x 45 N
Dimensional Stability AATCC 135	≤ 3.0%	≤ 3.0%
LAUNDERING TESTING	450	600
Piling Resistance 30 minutes 60 minutes 90 minutes 120 minutes ASTM 3512, Rating: 5 Best, 3 Acceptable, 1 Poor	4 5 5 5	4 5 5 5
Wicking 0.5 inch 1.0 inch 1.5 inch 2.0 inch	5.0 sec 15.0 sec 35.0 sec 63.0 sec	5.0 sec 12.0 sec 28.0 sec 59.0 sec
Washing Colorfastness (After 25 Launderings) 14°F (60°C) Industrial Wash, 160°F Max Stack Dry	4	4
Air Permeability	210 ft <sup>3</sup> /ft <sup>2</sup> /min	80 ft <sup>3</sup> /ft <sup>2</sup> /min
Colorfastness to Xenon Light (20 Hours) AATCC 16, Rating: 5 Best, 3 Acceptable, 1 Poor	3 - 4	3 - 4

\* All values subject to final certification and specification.

\*\* Tested on specific colors.

STANDARD COLORS			
Navy	Spruce Green	Gray	Royal Blue
Light Blue	Orange	Red	Yellow

## OPTIONAL COLORS

TenCate Protective Fabric, the world's textile dyeing expert, can produce almost every color with a minimum quantity of 3000 yards. Smaller quantities can be ordered, subject to a surcharge. For more information, please contact TenCate Protective Fabrics.

